



Interlam Lustre™ UV 75µ (3 mil)

Product Description

Interlam Lustre™ UV 75µ is a 50µ (2 mil) plasticised, UV stabilised, lustre finish, clear PVC overlaminating film coated on one side with a pressure sensitive, aqueous acrylic adhesive which is protected by a bleached Kraft green grid release paper coated on one side with siliconised polyethylene. Available in various sizes.

Suggested Applications

Interlam Lustre™ is recommended for photographic quality images that will be viewed under direct lighting conditions for indoor applications. Low sheen without loss of contrast or sharpness makes the 75µ (3mil) Interlam Lustre™ effective over a wide range of applications.

Product Structure

Film:	Lustre (Satin) PVC	75µ (3 mil)
Adhesive:	Aqueous Acrylic (Pressure Sensitive)	
Release Liner:	1 Side PE coated bleached Kraft Green Grid Paper (Moisture Stable)	

General Properties

Film Thickness	50µ (2mil)
Adhesive Layer	25µ (1mil)
Ratio Film/Adhesive	2/1
UV Protection Factor	Film contains U.V. stabilisers, which prevent film degradation and provides some U.V. protection to the underlying image.
Outdoor Durability	Not Applicable
Heat Resistance Range	70°C to 95°C (158°F to 203°F)
Peel Strength (20 min, FTM1)	23 N/25mm

Process Settings

Roller Laminator	Press
Temperature: Room temperature to 49°C (120°F) Speed: 0.3m to 1.75m (1 ft to 6 ft) per minute	NOT RECOMMENDED

Specifications subject to change without notice.

Published information concerning Drytac products is based upon research which the company believes to be reliable and accurate. Such information is intended only as a guide and is given without guarantees. Purchasers should independently determine, prior to use, the suitability of each material for their specific purpose. Drytac does not accept liability for risks associated with the performance of the materials in application. All Drytac products are subjected to carefully quality control throughout the manufacturing process and are sold subject to Drytac standard conditions of sale

Drytac Europe Ltd (UK) – Drytac House, Filwood Road, Fishponds, Bristol, BS16 3RY, UK. Tel: +44 (0) 845-070-0660

Drytac Corp. (USA) – 5383 Glen Alden Drive, Richmond, Virginia 23231, USA. Telephone: 1-800-603-6610

Drytac Canada Inc. (Canada) – 220 Caldari Road, Concord, Ontario, L4K 3X5, Canada. Telephone: 1-800-353-288