



## Protac Eclipse™ 330μ (13.2 mil)

### Product Description

Protac Eclipse™ 330μ (13.2 mil) is a 305μ (12.2 mil) opaque, white polyester backing film coated on one side with a pressure sensitive, solvent acrylic adhesive, which is protected by a 36μ (1.4 mil) natural polyester film with a single side easy release coating. Available in various sizes.

### Suggested Applications

Protac Eclipse™ 330μ (13.2 mil) is excellent for fully supported graphics. The combination of Eclipse and a reverse print media creates a durable graphic with excellent hanging characteristics, free from edge curl and fraying. The graphic can be rolled for shipping without fear of tunnelling.

### Product Structure

Film	305mic White Polyester with an opaque layer.
Adhesive:	Solvent Acrylic (Pressure Sensitive)
Release:	36mic Polyester (Moisture Stable)

### General Properties

Film Thickness	305μ (12.2 mil)
Adhesive Layer	25μ (1 mil)
Ratio Film/Adhesive	12/1

Heat resistance	Up 130°C (266°F)
Peel Strength (20 min, FTM1)	22N/25mm

### Process Settings

<b>Roller Laminator</b>	<b>Press</b>
Temperature: Room temperature to 49°C (120°F) Speed: 0.3m to 1.75m (1 ft to 6 ft) per minute	NOT RECOMMENDED

Specifications subject to change without notice.

Published information concerning Drytac products is based upon research which the company believes to be reliable and accurate. Such information is intended only as a guide and is given without guarantees. Purchasers should independently determine, prior to use, the suitability of each material for their specific purpose. Drytac does not accept liability for risks associated with the performance of the materials in application. All Drytac products are subjected to carefully quality control throughout the manufacturing process and are sold subject to Drytac standard conditions of sale

Drytac Europe Ltd (UK) – Drytac House, Filwood Road, Fishponds, Bristol, BS16 3RY, UK. Tel: +44 (0) 845-070-0660  
Drytac Corp. (USA) – 5383 Glen Alden Drive, Richmond, Virginia 23231, USA. Telephone: 1-800-603-6610  
Drytac Canada Inc. (Canada) – 220 Caldari Road, Concord, Ontario, L4K 3X5, Canada. Telephone: 1-800-353-288

<http://www.drytac.com>