



Protac™ High Gloss UV 100μ (4 mil)

Product Description

Protac™ High Gloss UV 100μ (4 mil) is a 75μ (3 mil) high gloss finish, clear polyester overlaminating film coated on one side with a pressure sensitive, solvent acrylic adhesive, which is protected by a 36μ natural polyester film with a single side easy release coating. Available in various sizes.

Suggested Applications

Protac™ High Gloss UV adds depth and detail to any image whether it is photographic, inkjet, electrostatic or other output media. Protac™ High Gloss is also the recommended film for photographic prints, POP graphics, or anywhere a high-gloss, almost mirror-like, finish is desired.

Product Structure

Film:	High Gloss Polyester	^ (4 mil) v 100μ
Adhesive:	Solvent Acrylic (Pressure Sensitive)	
Release Liner:	Polyester (Moisture Stable)	

General Properties

Film Thickness	75μ (3 mil)
Adhesive Layer	25μ (1mil)
Ratio Film/Adhesive	3/1
UV Protection Factor	Film contains U.V. stabilisers, which prevent film degradation and provides some U.V. protection to the underlying image.
Outdoor Durability	6 months will only show inconsequential changes in properties of this product.
Heat Resistance Range	Up 130°C (266°F)
Peel Strength (20 min, FTM1)	12 N/25mm

Process Settings

Roller Laminator	Press
Temperature: Room temperature to 49°C (120°F) Speed: 0.3m to 1.75m (1 ft to 6 ft) per minute	NOT RECOMMENDED

Specifications subject to change without notice.

Published information concerning Drytac products is based upon research which the company believes to be reliable and accurate. Such information is intended only as a guide and is given without guarantees. Purchasers should independently determine, prior to use, the suitability of each material for their specific purpose. Drytac does not accept liability for risks associated with the performance of the materials in application. All Drytac products are subjected to carefully quality control throughout the manufacturing process and are sold subject to Drytac standard conditions of sale

Drytac Europe Ltd (UK) – Drytac House, Filwood Road, Fishponds, Bristol, BS16 3RY, UK. Tel: +44 (0) 845-070-0660

Drytac Corp. (USA) – 5383 Glen Alden Drive, Richmond, Virginia 23231, USA. Telephone: 1-800-603-6610

Drytac Canada Inc. (Canada) – 220 Caldari Road, Concord, Ontario, L4K 3X5, Canada. Telephone: 1-800-353-288