



## Protac Sheentex™ UV 105μ (4.2 mil)

### Product Description

Protac Sheentex™ 105μ (4.2 mil) is a 80μ (3.2mil) plasticised, embossed, UV stabilised, satin pebble finish, clear PVC overlaminating film coated on one side with a pressure sensitive, solvent acrylic adhesive, which is protected by a bleached Kraft release paper (moisture stable) coated on both sides with polyethylene and siliconised on the release side. Available in various sizes.

### Suggested Applications

Protac Sheentex™ is the ideal film for mounted prints that will be placed in high traffic indoor display areas. It is also suitable for laminating placemats, counter pads and other similar applications.

### Product Structure

Film:	Pebble Textured Satin PVC	
Adhesive:	Solvent Acrylic (Pressure Sensitive)	
Release Paper:	2 Side PE Coated Bleached Woodfree Paper (Moisture Stable)	

### General Properties

Film Thickness	80μ (3.2 mil)
Adhesive Layer	25μ (1mil)
Ratio Film/Adhesive	3.2/1
UV Protection Factor	Film contains U.V. stabilisers, which prevent film degradation and provides some U.V. protection to the underlying image.
Outdoor Durability	3 months will only show inconsequential changes in properties of this product.
Heat resistance	70°C to 95°C (158°F to 203°F)
Peel Strength (20 min, FTM1)	12 N/25mm

### Process Settings

<b>Roller Laminator</b> Temperature: Room temperature to 49°C (120°F) Speed: 0.3m to 1.75m (1 ft to 6 ft) per minute	<b>Press</b> NOT RECOMMENDED
--	---------------------------------

Specifications subject to change without notice.

Published information concerning Drytac products is based upon research which the company believes to be reliable and accurate. Such information is intended only as a guide and is given without guarantees. Purchasers should independently determine, prior to use, the suitability of each material for their specific purpose. Drytac does not accept liability for risks associated with the performance of the materials in application. All Drytac products are subjected to carefully quality control throughout the manufacturing process and are sold subject to Drytac standard conditions of sale

Drytac Europe Ltd (UK) – Drytac House, Filwood Road, Fishponds, Bristol, BS16 3RY, UK. Tel: +44 (0) 845-070-0660  
 Drytac Corp. (USA) – 5383 Glen Alden Drive, Richmond, Virginia 23231, USA. Telephone: 1-800-603-6610  
 Drytac Canada Inc. (Canada) – 220 Caldari Road, Concord, Ontario, L4K 3X5, Canada. Telephone: 1-800-353-288