




ArtShield Canvastex™ UV 125m (5 mil)

PRODUCT DESCRIPTION: ArtShield Canvastex™ UV 125μ (5 mil) is a 100μ (4 mil) plasticised, embossed, UV stabilised, canvas finish, clear PVC overlaminating film coated on one side with a heat activated solvent acrylic adhesive, which is protected by a bleached Kraft grey grid release paper coated on one side with siliconised polyethylene. Available in various sizes.

SUGGESTED APPLICATIONS: The textured non-glare finish of ArtShield Canvastex™ UV is ideal for framed portraits, diplomas, and certificates. It is recommended not to put release paper on the top of the Artshield Canvastex™ UV when processing in a press as it may adversely affect the textured finish of the film.

PRODUCT STRUCTURE:



GENERAL PROPERTIES:

Film Thickness: 100μ (4 mil)
Adhesive Layer: 25μ (1mil)
Ratio Film/Adhesive: 4/1
UV Protection Factor 2: Film contains U.V. stabilisers, which prevent film degradation and provides some U.V. protection to the underlying image.
Outdoor durability: 3 months will only show inconsequential changes in properties of this product.
Heat Resistance Range: 70°C to 95°C (158°F to 203°F)
Peel Strength (20 min, FTMI): 18 N/25mm

PROCESS SETTINGS:

ROLLER LAMINATOR	PRESS
NOT RECOMMENDED	<i>Temperature range:</i> 85°C to 99°C (185°F to 210°F) <i>Dwell time:</i> 4 to 10 minutes

Specifications subject to change without notice. Published information concerning Drytac products is based upon research which the company believes to be reliable and accurate. Such information is intended only as a guide and is given without guarantees. Purchasers should independently determine, prior to use, the suitability of each material for their specific purpose. Drytac does not accept liability for risks associated with the performance of the materials in application. All Drytac products are subjected to carefully quality control throughout the manufacturing process and are sold subject to Drytac standard conditions of sale.

Drytac Europe Ltd (UK) – Drytac House, Filwood Road, Fishponds, Bristol, BS16 3RY, UK.
 Tel: +44 (0) 845-070-0660
Drytac Corp. (USA) – 5383 Glen Alden Drive, Richmond, Virginia 23231, USA.
 Telephone: 1-800-603-6610
Drytac Canada Inc. (Canada) – 137 Buttermill Avenue, Concord, Ontario, L4K 3X5, Canada.
 Telephone: 1-800-353-2883
www.drytac.com